

Guangzhou Huiming Fibre Products Co.,Ltd

Address: Xinwei Yutang Industry Park,Xiaotang,Shabu Village,

Nangang Town, Huangpu District, Guangzhou, PRC, 510760

Tel: +86 - 020 - 82252858 Fax: +86 - 020 - 82250789 Website:<http://hmxianwei.ecomgear.com>

	SPECIFICATIONS	
	260GSM MEMBRANE	
Filtermaterial		100% Polyester
Construction		Spunbond
Treatment		PTFE MEMBRANE
Permeability	m3/m2/h at 200 pa	190
Weight	g/m2	260
Elongation MD	%	18,6
Elongation CD	%	24,8
Thickness in mm	mm	0,56
Fiber size	Denier	1,2
Tenstile Strength MD	N	512,4
Tenstile Strength CD	N	518,3
Tear Strength MD	N	386,7
Tear Strength CD	N	357,2
Thermal Shrinkage MD	%	0,67
Thermal Shrinkage CD	%	0,32
Mullen Burst	Kg/cm2	25
Temperature Resistance	C	120
Hydrophobic Resist		GOOD
Acid Resistance		GOOD
Alkaline Resistance		GOOD
Dust Release		EXCELLENT
Filter Test	BIA	M
Efficiency of 0,3 Micron	%	97